

# SPS



## EASYTEX 3030 EXTRA MAT

### Extra matt flawless finish wall paint



- Leaves no traces from roller or brush
- Long open time
- Good coverage
- Extra matt: <math><1\%</math> at 85°
- Breathable and odourless

# EASYTEX 3030 EXTRA MAT

## DESCRIPTION

Extra matt wall paint which leaves no traces from roller and brush. Ideal for a perfect finish on walls and ceilings.

## RECOMMENDED USE

Highly suitable for painting walls and ceilings in new construction and renovation projects. Suitable substrates include: existing wall paint layers or cement and plaster, concrete, stone, gypsum board, etc., which have been properly pre-treated. Also very suitable for painting on glass fabric. For indoor use.

## RECOMMENDED SYSTEM

**New, untreated substrates** - Prime highly absorbent substrates completely with SPS Fix primer. - Clean powdery substrates thoroughly. Pre-treat with SPS Fix Primer after drying. - Paint over **existing intact wall paints** - Thoroughly clean. - Remove loose particles. - Thoroughly wash off any powdering layers and allow to dry. - Make any necessary repairs. - Pre-treat with SPS Fix-Primer. - After drying, paint over the surface. **Contamination by nicotine, moisture, rust or soot** - Clean thoroughly. - Treat the surface/contamination with SPS Iso-Primer. - Paint over the surface after drying. The above systems are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,51
Gloss Level:	Extra-Matt
Gloss level at 85°:	<1%, extra matt.
Solids Content in weight:	58,6
Solids content in volume:	38,7

## DRY TIMES BY 20° C/RH 50%

Touch dry:	2 hours
Dry to recoat:	6 hours
Fully cured:	After 24 hours.

## RECOMMENDED WET FILM THICKNESS

130 micrometres

## RECOMMENDED DRY FILM THICKNESS

50 micrometres

## THEORETICAL CONSUMPTION

Approx. 8 m<sup>2</sup>/l per coat. The stated yield is theoretical.

## PRACTICAL CONSUMPTION

Actual consumption depends on the nature and structure of the substrate and the processing method.

## SURFACE PREPARATION

The substrate must be load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

## DIRECTIONS FOR USE

Stir well before use. If necessary, dilute the first coat with max. 5% water. Apply in 1 or 2 layers, using a suitable brush or roller. For optimum results, apply in at least 2 layers. Always work wet-on-wet to avoid swelling. Re-roll all webs in the same direction. Do not touch up while drying.

## APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature.

## APPLICATION & THINNING: BRUSH

Ready-to-use.

## APPLICATION & THINNING: ROLLER

Ready-to-use.

## APPLICATION & THINNING: AIRLESS SPRAY

Airless: nozzle: 0.017" - 0.021" and pressure: 180 bar. Airmix: nozzle: 0.015" - 0.019", pressure: 125 bar and air pressure: 1.5 bar.

The specified settings for spraying this product are a starting point. Depending on site conditions, the settings will have to be determined by the applicator.

## CLEANING OF EQUIPMENT / SPILLS

Water and soap.

## REMARKS

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale vapour and spray of products. Dispose of this material and its container to hazardous or special waste collection point.

When drying this product, slight (gloss) bumps and lane formation, caused by insufficient paint distribution, must disappear. If this is not the case, an additional coat should be applied. Variations in layer thickness, temperature, humidity, etc. will affect drying time, gloss level and flow.

## SHELF LIFE

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Date issued: 11/05/2026

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu

