

# SPS



## EASYTOP EXTRA MAT

# Extra matt flawless finish wall paint

- Leaves no traces from roller or brush
- Long open time
- Good coverage
- Extra matt: <math><1\%</math> at 85
- Breathable and odourless

# EASYTOP EXTRA MAT

## ОПИСАНИЕ

Extra matt wall paint which leaves no traces from roller and brush. Ideal for a perfect finish on walls and ceilings.

## ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

Highly suitable for painting walls and ceilings in new construction and renovation projects. Suitable substrates include: existing wall paint layers or cement and plaster, concrete, stone, gypsum board, etc., which have been properly pre-treated. Also very suitable for painting on glass fabric. For indoor use.

## ПРЕПОРЪЧИТЕЛНА СИСТЕМА

**New, untreated substrates** - Prime highly absorbent substrates completely with SPS Fix primer. - Clean powdery substrates thoroughly. Pre-treat with SPS Fix Primer after drying. - Paint over **existing intact wall paints** - Thoroughly clean. - Remove loose particles. - Thoroughly wash off any powdering layers and allow to dry. - Make any necessary repairs. - Pre-treat with SPS Fix-Primer. - After drying, paint over the surface. **Contamination by nicotine, moisture, rust or soot** - Clean thoroughly. - Treat the surface/contamination with SPS Iso-Primer. - Paint over the surface after drying. The above systems are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

## ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см <sup>3</sup> ):	1,51
Гланцово ниво:	extra_matt
gloss_level_85:	<1%
Съдържание на сухо вещество (по тегло):	58,6
Съдържание на сухо вещество (по обем):	38,7

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	2 hours
Готов за повторно нанасяне:	6 hours
group_dry_40_full_cure:	24 hours

## МОКЪР СЛОЙ

130 micrometres

## СУХ СЛОЙ

50 micrometres

## РАЗХОДНА НОРМА

Approx. 8 m<sup>2</sup>/l per coat. The stated yield is theoretical.

## КОНСУМАЦИЯ

Actual consumption depends on the nature and structure of the substrate and the processing method.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

## НАЧИН НА УПОТРЕБА

Stir well before use. If necessary, dilute the first coat with max. 5% water. Apply in 1 or 2 layers, using a suitable brush or roller. For optimum results, apply in at least 2 layers. Always work wet-on-wet to avoid swelling. Re-roll all webs in the same direction. Do not touch up while drying.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Ready-to-use.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Ready-to-use.

## БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Airless: nozzle: 0.017" - 0.021" and pressure: 180 bar. Airmix: nozzle: 0.015" - 0.019", pressure: 125 bar and air pressure: 1.5 bar. The specified settings for spraying this product are a starting point. Depending on site conditions, the settings will have to be determined by the applicator.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap.

## ЗАБЕЛЕЖКИ

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale vapour and spray of products. Dispose of this material and its container to hazardous or special waste collection point. When drying this product, slight (glossy) bumps and striping, caused by insufficient paint distribution, must disappear. If this is not the case, an additional coat should be applied. Variations in layer thickness, temperature, humidity, etc. will affect drying time, gloss level and flow.

## СРОК НА ГОДНОСТ

Minimum 12 months in well-sealed original packaging.

Дата на издаване: 27/05/2026

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

