

SPS



GLOSS AE

High gloss paint based on a PU modified alkyd emulsion

- Resistant to oils from the skin
- Long-lasting retention of colour and gloss
- High durability
- Attractive, high-build gloss
- Easy to apply with brush

GLOSS AE

ОПИСАНИЕ

Durable, high gloss, water-based top coat paint based on a polyurethane modified alkyd emulsion. Virtually odourless, solvent-free and quick drying. Attractive, high-gloss finish with a high build and long-lasting colour retention. Easy to work with a brush, resistant to oils from the skin and high durability. For interior and exterior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

As a top coat paint on pre-treated wood substrates. In addition, as a top coat paint on pre-treated plastic or metal substrates.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

General: The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage.

Exposed/untreated wood

- Prime untreated wood with SPS Multiprimer and types of wood that bleed with SPS Primer ISO.

- Allow to dry, lightly sand and remove dust.

- Apply top coat paint.

Existing old coats

- Remove old loose coats.

- Clean the entire surface using SPS Paint cleaner.

- Sand decayed wood down to healthy wood before applying primer.

- Carry out any repairs and prime.

- Allow to dry, sand and remove dust.

- Prime exposed areas with SPS Multiprimer or, in the case of types of woods that bleed, with SPS Primer ISO.

- Allow to dry, lightly sand and remove dust.

- Apply top coat paint.

Existing intact coats of paint

- Clean the intact coats using SPS Paint cleaner

- Sand the surface well.

- Touch up with primer or apply a complete coat of primer using SPS Multiprimer.

- Allow to dry, lightly sand and remove dust.

- Paint to cover.

The systems stated above generally describe the most frequently occurring surfaces. For specific applications and/or detailed advice, please contact SPS bv.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см ³):	1.23
Гланцово ниво:	sps_hoogglans
Гланцово ниво при 60°:	90%
Съдържание на сухо вещество (по обем):	33%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	1 hour
Готов за повторно нанасяне:	16 hours

МОКЪР СЛОЙ

67 µm

СУХ СЛОЙ

23 µm

РАЗХОДНА НОРМА

approx. 15 m² /litre per coat

КОНСУМАЦИЯ

The actual coverage depends on the nature and the structure of the surface and the application method.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

НАЧИН НА УПОТРЕБА

Stir thoroughly prior to use. Apply in 1 or 2 coats using a suitable brush or paint roller. Water-based products dry relatively quickly. Always work wet-on-wet to prevent visible brush strokes. Do not touch up when drying.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Always ventilate appropriately when applying. Products based on alkyd resins tend to yellow in a dark environment or when covered. In an environment where they are exposed to daylight, this tendency to yellow is much reduced. This SPS product is resistant to skin oils. The degree of resistance to skin oils of the paint coats depends on the type of surface contamination and exposure time. Regular cleaning using a suitable cleaning agent extends the life of the paint coat.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Ready-to-use.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Ready-to-use.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Use water and soap.

ЗАБЕЛЕЖКИ

СРОК НА ГОДНОСТ

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Дата на издаване: 27/05/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

