

# SPS



## HIGH GLOSS SB

### High-gloss top coat based on a siliconized alkyd resin

- Perfect flow
- Long-lasting gloss retention
- High durability
- Easy to apply with brush
- Attractive, high-build gloss

# HIGH GLOSS SB

## ОПИСАНИЕ

High-gloss top coat paint based on a siliconized alkyd resin offering long-lasting protection and a durable gloss finish. SPS High Gloss SB paint offers high hiding power, perfect flow and an attractive, high-build gloss. Maximum durability in combination with SPS Primer LS. For exterior use.

## ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

As a highly durable top coat on pre-treated wood, metal or plastic substrates

## ПРЕПОРЪЧИТЕЛНА СИСТЕМА

**General:** The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage.

### Exposed/untreated wood

- Prime untreated wood using SPS Primer HS.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint. Existing old coats
- Remove old loose coats.
- Clean the entire surface using SPS Paint cleaner.
- Sand decayed wood down to healthy wood before applying primer.
- Carry out any repairs and prime.
- Allow to dry, sand and remove dust.
- Prime exposed parts using SPS Primer HS.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

### Existing intact coats of paint

- Clean the intact coats using SPS Paint cleaner
- Sand the surface well.
- Touch up with primer or apply a complete coat of primer using SPS Primer HS. - Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

The systems stated above generally describe the most frequently occurring surfaces. For specific applications and/or detailed advice, please contact SPS bv.

## ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см <sup>3</sup> ):	1.15
Гланцово ниво:	sps_hoogglans
Гланцово ниво при 60°:	> 80%
Съдържание на сухо вещество (по обем):	65%

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	4 hours
Готов за повторно нанасяне:	20 hours

## МОКЪР СЛОЙ

60 µm

## СУХ СЛОЙ

40 µm

## РАЗХОДНА НОРМА

Approx. 14-16 m<sup>2</sup>/litre per coat

## КОНСУМАЦИЯ

The actual coverage depends on the nature and the structure of the surface and the application method.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

## НАЧИН НА УПОТРЕБА

Stir thoroughly prior to use. Apply in 1 or more coats using a suitable brush or paint roller. Always work wet-on-wet to prevent visible brush strokes. Do not touch up when drying. Lightly sand and remove any dust between the coats.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Always ventilate appropriately when applying. Products based on alkyd resins tend to yellow in a dark environment or when covered. In an environment where they are exposed to daylight, this tendency to yellow is much reduced.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Ready-to-use.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Ready-to-use.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

White spirit or brush cleaner

## ЗАБЕЛЕЖКИ

Variations in coating thickness, temperature, humidity, etc. affect the drying time.

## СРОК НА ГОДНОСТ

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Дата на издаване: 27/05/2026

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu

