

SPS



HIGH GLOSS SB

High-gloss top coat based on a siliconized alkyd resin

- Perfect flow
- Long-lasting gloss retention
- High durability
- Easy to apply with brush
- Attractive, high-build gloss

HIGH GLOSS SB

DESCRIPTION

High-gloss top coat paint based on a siliconized alkyd resin offering long-lasting protection and a durable gloss finish. SPS High Gloss SB paint offers high hiding power, perfect flow and an attractive, high-build gloss. Maximum durability in combination with SPS Primer LS. For exterior use.

RECOMMENDED USE

As a highly durable top coat on pre-treated wood, metal or plastic substrates

RECOMMENDED SYSTEM

General: The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage.

Exposed/untreated wood

- Prime untreated wood using SPS Primer HS.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint. Existing old coats
- Remove old loose coats.
- Clean the entire surface using SPS Paint cleaner.
- Sand decayed wood down to healthy wood before applying primer.
- Carry out any repairs and prime.
- Allow to dry, sand and remove dust.
- Prime exposed parts using SPS Primer HS.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

Existing intact coats of paint

- Clean the intact coats using SPS Paint cleaner
- Sand the surface well.
- Touch up with primer or apply a complete coat of primer using SPS Primer HS. - Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

The systems stated above generally describe the most frequently occurring surfaces. For specific applications and/or detailed advice, please contact SPS bv.

TECHNICAL DATA

Density (g/cm ³):	1.15
Gloss Level:	sps_hoogglans
Gloss level at 60°:	> 80%
Solids content in volume:	65%

DRY TIMES BY 20° C/RH 50%

Touch dry:	4 hours
Dry to recoat:	20 hours

RECOMMENDED WET FILM THICKNESS

60 µm

RECOMMENDED DRY FILM THICKNESS

40 µm

THEORETICAL CONSUMPTION

Approx. 14-16 m²/litre per coat

PRACTICAL CONSUMPTION

The actual coverage depends on the nature and the structure of the surface and the application method.

SURFACE PREPARATION

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

DIRECTIONS FOR USE

Stir thoroughly prior to use. Apply in 1 or more coats using a suitable brush or paint roller. Always work wet-on-wet to prevent visible brush strokes. Do not touch up when drying. Lightly sand and remove any dust between the coats.

APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Always ventilate appropriately when applying. Products based on alkyd resins tend to yellow in a dark environment or when covered. In an environment where they are exposed to daylight, this tendency to yellow is much reduced.

APPLICATION & THINNING: BRUSH

Ready-to-use.

APPLICATION & THINNING: ROLLER

Ready-to-use.

CLEANING OF EQUIPMENT / SPILLS

White spirit or brush cleaner

REMARKS

Variations in coating thickness, temperature, humidity, etc. affect the drying time.

SHELF LIFE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date issued: 27/05/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

