

# SPS



## **MAT PU-A**

### **Matt PU acrylic paint**

- Resistant to oils from the skin
- Good retention of colour and gloss
- Perfect flow
- Scratch-resistant
- Virtually odourless and quick drying

# MAT PU-A

## DESCRIPTION

Water-based, durable, scratch-resistant and matt PU acrylic paint with good retention of colour. For a decorative finish on wood, hard plastics and metal. Resistant to oils from the skin, quick drying, odourless and low in solvents. For interior use.

## RECOMMENDED USE

As a top coat paint on pre-treated wood substrates. In addition, as a top coat paint on pre-treated plastic or metal substrates.

## RECOMMENDED SYSTEM

**General:** The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage.

### Exposed/untreated wood

- Prime untreated wood with SPS Multiprimer and types of wood that bleed with SPS Primer ISO.

- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

### Existing old coats

- Remove old loose coats.
- Clean the entire surface using SPS Paint cleaner.
- Sand decayed wood down to healthy wood before applying primer.
- Carry out any repairs and prime.
- Allow to dry, sand and remove dust.
- Prime exposed areas with SPS Multiprimer or, in the case of types of woods that bleed, with SPS Primer ISO.

- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

### Existing intact coats of paint

- Clean the intact coats using SPS Paint cleaner
- Sand the surface well.
- Touch up with primer or apply a complete coat of primer using SPS Multiprimer.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1.23
Gloss Level:	Matt
Gloss level at 60°:	5-10%
Solids content in volume:	37%

## DRY TIMES BY 20° C/RH 50%

Touch dry:	After approx.30 minutes
Dry to recoat:	6 hours

## RECOMMENDED WET FILM THICKNESS

67 µm

## RECOMMENDED DRY FILM THICKNESS

25 µm

## THEORETICAL CONSUMPTION

14-16 m<sup>2</sup>/litre per coat

## PRACTICAL CONSUMPTION

The actual coverage depends on the nature and the structure of the surface and the application method.

## SURFACE PREPARATION

The substrate must be load-bearing, clean, dry, dust- and grease-free. Slightly round off sharp corners to achieve good edge coverage.

## DIRECTIONS FOR USE

Stir thoroughly prior to use. Apply in 1 or 2 coats using a suitable brush or paint roller. Water-based products dry relatively quickly. Always work wet-on-wet to prevent visible brush strokes. Do not touch up when drying.

## APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Always ventilate appropriately when applying. Products based on alkyd resins tend to yellow in a dark environment or when covered. In an environment where they are exposed to daylight, this tendency to yellow is much reduced. This SPS product is resistant to skin oils. The degree of resistance to skin oils of the paint coats depends on the type of surface contamination and exposure time. Regular cleaning using a suitable cleaning agent extends the life of the paint coat.

## APPLICATION & THINNING: BRUSH

Ready-to-use.

## APPLICATION & THINNING: ROLLER

Ready-to-use.

## CLEANING OF EQUIPMENT / SPILLS

Use water and soap

## REMARKS

Variations in layer thickness, temperature, humidity, etc. affect the drying time. Lower temperature and higher humidity may delay drying. This SPS product is skin grease resistant. Skin grease resistance of paint layers should take into account the nature of surface contamination and exposure time. Regular cleaning with a suitable agent will thereby extend the service life of the paint layer.

## SHELF LIFE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date issued: 27/05/2026

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
info@rust-oleum.eu

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
info@rust-oleum.eu

