



SPS



MULTIMAT

Multi-purpose matt wall paint

- For interior and protected exterior use
- Scrub-resistant, class 1 (DIN EN 13300)
- Good sprayability and rollability
- Good coverage
- Matte finish

MULTIMAT

ОПИСАНИЕ

Versatile matte wall paint based on acrylic dispersion.

Scrub-resistant, class 1. Easy to apply and provides good coverage.

Perfectly suited for painting walls and ceilings in large new-build and renovation projects.

For interior and sheltered exterior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

Ideally suited for painting walls and ceilings in large-scale new-build and renovation projects. Suitable substrates include: existing wall paint, cement and plasterwork, concrete, brick, plasterboard, etc. For indoor use and sheltered outdoor work. SPS Multimat can be applied to dry and fully set mineral substrates. The moisture content of mineral substrates must not exceed 4%. The moisture content of gypsum-based substrates must not exceed 1%. Application to substrates that are not fully set may result in colour variation (due to lime bleed). In severe cases, this may lead to damage to the paint.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

New, untreated substrates - Prime highly absorbent substrates completely with SPS Fix primer. - Clean powdery substrates thoroughly. Pre-treat with SPS Fix Primer after drying. - Paint over **existing intact wall paints** - Thoroughly clean. - Remove loose particles. - Thoroughly wash off any powdering layers and allow to dry. - Make any necessary repairs. - Pre-treat with SPS Fix-Primer. - After drying, paint over the surface. **Contamination by nicotine, moisture, rust or soot** - Clean thoroughly. - Treat the surface/contamination with SPS Iso-Primer. - Paint over the surface after drying. The above systems are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1,45
Гланцово ниво:	Мат
gloss_level_85:	5%, extra matt
Съдържание на сухо вещество (по обем):	40%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	1 hour
Готов за повторно нанасяне:	4 - 6 hours

МОКЪР СЛОЙ

Approx. 125 micrometers

СУХ СЛОЙ

Approx. 50 micrometers

РАЗХОДНА НОРМА

Approx.. 8 m²/ l per coat

КОНСУМАЦИЯ

Actual consumption depends on the nature and structure of the substrate and the processing method.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

НАЧИН НА УПОТРЕБА

Stir well before use. If necessary, dilute the first coat with max. 10% water. Apply in 1 or 2 layers, using a suitable brush or roller. For optimum results, apply in at least 2 layers. Always work wet-on-wet to avoid swelling. Re-roll all webs in the same direction. Do not touch up while drying.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Ready for use

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Ready for use

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Airless: nozzle: 0.015" - 0.017" and pressure: 180 bar.

Airmix: nozzle: 0.015" - 0.017", pressure: 125 bar and air pressure: 1.5 bar.

The specified settings for spraying this product are a starting point. Depending on site conditions, the settings will have to be determined by the applicator.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap

ЗАБЕЛЕЖКИ

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale vapour and spray of products. Dispose of this material and its container to hazardous or special waste collection point.

СРОК НА ГОДНОСТ

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Дата на издаване: 27/05/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

