



SPS



MULTIMAT

Multi-purpose matt wall paint

- For interior and protected exterior use
- Scrub-resistant, class 1 (DIN EN 13300)
- Good sprayability and rollability
- Good coverage
- Matte finish

MULTIMAT

DESCRIPTION

Versatile matte wall paint based on acrylic dispersion.

Scrub-resistant, class 1. Easy to apply and provides good coverage.

Perfectly suited for painting walls and ceilings in large new-build and renovation projects.

For interior and sheltered exterior use.

RECOMMENDED USE

Ideally suited for painting walls and ceilings in large-scale new-build and renovation projects. Suitable substrates include: existing wall paint, cement and plasterwork, concrete, brick, plasterboard, etc. For indoor use and sheltered outdoor work. SPS Multimatt can be applied to dry and fully set mineral substrates. The moisture content of mineral substrates must not exceed 4%. The moisture content of gypsum-based substrates must not exceed 1%. Application to substrates that are not fully set may result in colour variation (due to lime bleed). In severe cases, this may lead to damage to the paint.

RECOMMENDED SYSTEM

New, untreated substrates - Prime highly absorbent substrates completely with SPS Fix primer. - Clean powdery substrates thoroughly. Pre-treat with SPS Fix Primer after drying. - Paint over **existing intact wall paints** - Thoroughly clean. - Remove loose particles. - Thoroughly wash off any powdering layers and allow to dry. - Make any necessary repairs. - Pre-treat with SPS Fix-Primer. - After drying, paint over the surface. **Contamination by nicotine, moisture, rust or soot** - Clean thoroughly. - Treat the surface/contamination with SPS Iso-Primer. - Paint over the surface after drying. The above systems are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

TECHNICAL DATA

Density (g/cm ³):	1,45
Gloss Level:	Matt
Gloss level at 85°:	5%, extra matt
Solids content in volume:	40%

DRY TIMES BY 20° C/RH 50%

Touch dry:	1 hour
Dry to recoat:	4 - 6 hours

RECOMMENDED WET FILM THICKNESS

Approx. 125 micrometers

RECOMMENDED DRY FILM THICKNESS

Approx. 50 micrometers

THEORETICAL CONSUMPTION

Approx.. 8 m²/ l per coat

PRACTICAL CONSUMPTION

Actual consumption depends on the nature and structure of the substrate and the processing method.

SURFACE PREPARATION

The substrate must be load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

DIRECTIONS FOR USE

Stir well before use. If necessary, dilute the first coat with max. 10% water. Apply in 1 or 2 layers, using a suitable brush or roller. For optimum results, apply in at least 2 layers. Always work wet-on-wet to avoid swelling. Re-roll all webs in the same direction. Do not touch up while drying.

APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature.

APPLICATION & THINNING: BRUSH

Ready for use

APPLICATION & THINNING: ROLLER

Ready for use

APPLICATION & THINNING: AIRLESS SPRAY

Airless: nozzle: 0.015" - 0.017" and pressure: 180 bar.

Airmix: nozzle: 0.015" - 0.017", pressure: 125 bar and air pressure: 1.5 bar.

The specified settings for spraying this product are a starting point. Depending on site conditions, the settings will have to be determined by the applicator.

CLEANING OF EQUIPMENT / SPILLS

Water and soap

REMARKS

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale vapour and spray of products. Dispose of this material and its container to hazardous or special waste collection point.

SHELF LIFE

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Date issued: 27/05/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

