



SPS



PRIMER LS

Semi-gloss primer based on modified alkyd resin

- For an optimal gloss result
- Very good flow
- Good edge coverage
- Semi-gloss appearance
- Good filling

PRIMER LS

ОПИСАНИЕ

Very good flowing semi-gloss primer based on modified alkyd resin. Thanks to its good flow and semi-matt appearance, it is ideal as primer and pre-paint in a paint system with a high- or satin-gloss finish. Available in all light colours in the colour mixing system. For exterior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

SPS Primer LS is especially suited as a midcoat in exterior situations which are exposed to normal atmospheric conditions. Because of the semi-gloss aspect and flow this product is perfect as a midcoat in a solvent based paint system which requires a high quality and high gloss finish.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

General: The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage.

Exposed/untreated wood

- Prime untreated wood using SPS Primer LS.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

Existing old coats

- Remove old loose coats.
- Clean the entire surface using a paint cleaner like Universol®.
- Sand decayed wood down to healthy wood before applying SPS Primer LS.
- Carry out any repairs and apply SPS Primer LS.
- Allow to dry, sand and remove dust.
- Prime exposed parts using SPS Primer LS.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

Existing intact coats of paint

- Clean the intact coats using a Paint cleaner like Universol®.
- Sand the surface well.
- Touch up with primer or apply a complete coat of primer using SPS Primer LS. - Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1.6
Гланцово ниво при 60°:	semi-matt
Съдържание на сухо вещество (по обем):	60%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	3 hours
Готов за повторно нанасяне:	18 hours

МОКЪР СЛОЙ

65 µm

СУХ СЛОЙ

40 µm

РАЗХОДНА НОРМА

Ca. 16 m²/litre per coat

КОНСУМАЦИЯ

The actual coverage depends on the nature and the structure of the surface and the application method.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be sound, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners of wooden window frames.

НАЧИН НА УПОТРЕБА

Stir well before use. This product is ready for use and needs no dilution. Apply evenly in 1 or 2 coats using a suitable brush or paint roller at the recommended film thickness. After drying sand lightly with a grain size of P180 - P280 and clean away the dust. After that finish with a SPS opaque/laquer.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not use at temperatures lower than +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Always ventilate appropriately when applying. Products based on alkyd resins tend to yellow in a dark environment or when covered. In an environment where they are exposed to daylight, this tendency to yellow is much reduced.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Ready-to-use.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Ready-to-use.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Use Turpentine/ White Spirit of brush cleaner

ЗАБЕЛЕЖКИ

SPS Primer LS has the capacity to be left unfinished for about one season in exterior situations which are exposed to normal atmospheric conditions, before it is finished with a top coat. When old coats are, locally, completely removed from carpentry, the substrate has to be primed with sufficient SPS Primer because the film thickness from the factory has to be matched.

СРОК НА ГОДНОСТ

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Дата на издаване: 27/05/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

