



SPS



PRIMER LS

Semi-gloss primer based on modified alkyd resin

- For an optimal gloss result
- Very good flow
- Good edge coverage
- Semi-gloss appearance
- Good filling

PRIMER LS

DESCRIPTION

Very good flowing semi-gloss primer based on modified alkyd resin. Thanks to its good flow and semi-matt appearance, it is ideal as primer and pre-paint in a paint system with a high- or satin-gloss finish. Available in all light colours in the colour mixing system. For exterior use.

RECOMMENDED USE

SPS Primer LS is especially suited as a midcoat in exterior situations which are exposed to normal atmospheric conditions. Because of the semi-gloss aspect and flow this product is perfect as a midcoat in a solvent based paint system which requires a high quality and high gloss finish.

RECOMMENDED SYSTEM

General: The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage.

Exposed/untreated wood

- Prime untreated wood using SPS Primer LS.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

Existing old coats

- Remove old loose coats.
- Clean the entire surface using a paint cleaner like Universol®.
- Sand decayed wood down to healthy wood before applying SPS Primer LS.
- Carry out any repairs and apply SPS Primer LS.
- Allow to dry, sand and remove dust.
- Prime exposed parts using SPS Primer LS.
- Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

Existing intact coats of paint

- Clean the intact coats using a Paint cleaner like Universol®.
- Sand the surface well.
- Touch up with primer or apply a complete coat of primer using SPS Primer LS. - Allow to dry, lightly sand and remove dust.
- Apply top coat paint.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

TECHNICAL DATA

Density (g/cm ³):	1.6
Gloss level at 60°:	semi-matt
Solids content in volume:	60%

DRY TIMES BY 20° C/RH 50%

Touch dry:	3 hours
Dry to recoat:	18 hours

RECOMMENDED WET FILM THICKNESS

65 µm

RECOMMENDED DRY FILM THICKNESS

40 µm

THEORETICAL CONSUMPTION

Ca. 16 m²/litre per coat

PRACTICAL CONSUMPTION

The actual coverage depends on the nature and the structure of the surface and the application method.

SURFACE PREPARATION

The substrate must be sound, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners of wooden window frames.

DIRECTIONS FOR USE

Stir well before use. This product is ready for use and needs no dilution. Apply evenly in 1 or 2 coats using a suitable brush or paint roller at the recommended film thickness. After drying sand lightly with a grain size of P180 - P280 and clean away the dust. After that finish with a SPS opaque/laquer.

APPLICATION CONDITIONS

Do not use at temperatures lower than +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Always ventilate appropriately when applying. Products based on alkyd resins tend to yellow in a dark environment or when covered. In an environment where they are exposed to daylight, this tendency to yellow is much reduced.

APPLICATION & THINNING: BRUSH

Ready-to-use.

APPLICATION & THINNING: ROLLER

Ready-to-use.

CLEANING OF EQUIPMENT / SPILLS

Use Turpentine/ White Spirit of brush cleaner

REMARKS

SPS Primer LS has the capacity to be left unfinished for about one season in exterior situations which are exposed to normal atmospheric conditions, before it is finished with a top coat. When old coats are, locally, completely removed from carpentry, the substrate has to be primed with sufficient SPS Primer because the film thickness from the factory has to be matched.

SHELF LIFE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date issued: 27/05/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu

