



# SPS



## PROJECTTEX 2020 MAT

# Ready mixed black project-wallpaint



- Deep black color
- For ceilings and walls
- Universally applicable

# ПРОЕКТТЕХ 2020 МАТ

## ОПИСАНИЕ

Well-covering wall paint for painting large new construction and renovation projects. Suitable for interior and exterior walls, and also ideal for giving ceilings in commercial buildings an industrial look.

## ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

Ideal for use on building projects. Designed specifically for painting walls and ceilings in large-scale new-build and renovation projects. Suitable surfaces include: existing wall paint, cement and plaster, concrete, brick, etc.

## ПРЕПОРЪЧИТЕЛНА СИСТЕМА

**New untreated substrates** - Thoroughly pre-treat highly absorbent substrates with SPS Fix Primer - Thoroughly clean powdery substrates. Pre-treat with SPS Fix-Primer after drying. - Paint over with opaque film after drying. **Existing intact wall paint layers** - Thoroughly clean - Paint over with opaque film after drying. **Existing non-load-bearing wall paint layers** - Remove loose particles - Wash off powdery layers thoroughly and allow to dry - Carry out repairs if necessary. - Pre-treat with SPS Fix-Primer - Once dry, paint over the entire surface. **Contamination by nicotine, moisture, rust or soot** - Thoroughly clean - Treat the surface/contamination with SPS Iso-Primer - Once dry, paint over the entire surface. The above systems are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

## ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см<sup>3</sup>): 1,50  
gloss\_level\_85: 7%, mat.  
Съдържание на сухо вещество (по обем): 45%

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир: 2 hours.  
Готов за повторно нанасяне: 4 - 6 hours.

## МОКЪР СЛОЙ

Approx. 146 micrometers.

## СУХ СЛОЙ

Approx. 64 micrometers.

## РАЗХОДНА НОРМА

Approx. 7 m<sup>2</sup> / l per coat

## КОНСУМАЦИЯ

Actual consumption depends on the nature and structure of the substrate and the processing method.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers. For exterior use, remove all algae and moss deposits.

## НАЧИН НА УПОТРЕБА

Stir well before use. If necessary, dilute the first coat with up to 10% water. Apply with a suitable brush, roller or sprayer. Always work wet-on-wet to avoid deposits. Re-roll all webs in the same direction. Do not touch up while drying.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors under threat of rain, frost or full sun.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Maximum 10% water.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Maximum 10% water.

## БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Airless Nozzle: 0.015"-0.019", Pressure: approx.200 bar, Dilute: Maximum 5% water.  
Airmix Nozzle: 0.017-0.019", Pressure: approx.160 bar, Air pressure: approx. 1.5 bar, Dilute: Maximum 5% water.

The specified settings for spraying this product apply as a starting point. Depending on site conditions, settings will have to be determined by the applicator.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap.

## ЗАБЕЛЕЖКИ

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always provide adequate ventilation during application. Dispose of residues of this material and its packaging to hazardous or special waste collection point.

## СРОК НА ГОДНОСТ

Minimum 12 months in tightly closed original container in dry, cool, frost-free place.

Дата на издаване: 27/05/2026

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителя е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

