

SPS



SATIN AE

Satin gloss top coat based on a PU modified alkyd emulsion

- Resistant to oils from the skin
- Long-lasting retention of colour and gloss
- High durability
- Attractive satin gloss
- Easy to apply with brush

SATIN AE

ОПИСАНИЕ

Durable, satin gloss, water-based top coat paint based on a polyurethane modified alkyd emulsion. Virtually odourless, solvent-free and quick drying. Long-lasting gloss and colour retention. Easy to work with a brush, resistant to oils from the skin and high durability. For interior and exterior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

General: The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

Bare untreated wood

- Prime untreated wood with SPS Multi-Primer, bleeding wood with SPS Acrylic Primer.
- Lightly sand and dust-free after drying.
- Paint off opaque coat.

Existing old layers

- Remove old, loose layers.
- Clean with a paint cleaner such as Universol®.
- Sand and prime greyed wood down to healthy wood.
- If necessary, repair and prime.
- After drying, sand and dust off.
- Prime bare parts with SPS Multi-Primer, bleeding wood with SPS Acrylic Primer.
- Lightly sand and dust off after drying.
- Paint over the entire surface.

Existing intact paint layers

- Clean intact coats with a paint cleaner such as Universol® - Sand the surface well.
- Prime with SPS Multi-Primer.
- Lightly sand and dust after drying.
- Paint over the surface.

The systems listed are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	1.25
Гланцово ниво:	sps_zijdeglans
Гланцово ниво при 60°:	45-50%
Съдържание на сухо вещество (по обем):	35%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	1 hour
Готов за повторно нанасяне:	16 hours

МОКЪР СЛОЙ

67 µm

СУХ СЛОЙ

23 µm

РАЗХОДНА НОРМА

Approx 15 m² / l per coat

КОНСУМАЦИЯ

The practical yield depends on several factors such as, among others: the nature and structure of the substrate, the processing method, experience of the processor, and the (weather) conditions during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

НАЧИН НА УПОТРЕБА

Stir well before use. Apply in 1 or 2 layers with a suitable brush or roller. Waterborne products dry relatively quickly. To avoid deposits, always work wet-on-wet. Do not touch up while drying.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors under threat of rain, frost or full sun. Always use the necessary personal protective equipment when applying this product. Alkyd resin-based products have the tendency to yellow in dark surroundings or when covered. In an environment exposed to daylight this phenomenon is much less common. Always ventilate appropriately during application. This product is skin fat resistant. For skin fat resistance of paint layers, the type of surface contamination and exposure time must be taken into account. Regular cleaning with a suitable agent will increase the service life of the paint film.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Ready-to-use.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Ready-to-use.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap

ЗАБЕЛЕЖКИ

Always use the necessary personal protective equipment when processing this product. Alkyd resin-based products have the tendency to yellow in dark surroundings or when covered. In an environment exposed to daylight this phenomenon is much less common. Always ventilate appropriately during application. This product is skin fat resistant. For skin fat resistance of paint layers, the type of surface contamination and exposure time must be taken into account. Regular cleaning with a suitable agent will increase the service life of the paint film.

СРОК НА ГОДНОСТ

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Дата на издаване: 27/05/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя своите продукти на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

