

SPS



SATIN AE

Satin gloss top coat based on a PU modified alkyd emulsion

- Resistant to oils from the skin
- Long-lasting retention of colour and gloss
- High durability
- Attractive satin gloss
- Easy to apply with brush

SATIN AE

DESCRIPTION

Durable, satin gloss, water-based top coat paint based on a polyurethane modified alkyd emulsion. Virtually odourless, solvent-free and quick drying. Long-lasting gloss and colour retention. Easy to work with a brush, resistant to oils from the skin and high durability. For interior and exterior use.

RECOMMENDED USE

RECOMMENDED SYSTEM

General: The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

Bare untreated wood

- Prime untreated wood with SPS Multi-Primer, bleeding wood with SPS Acrylic Primer.
- Lightly sand and dust-free after drying.
- Paint off opaque coat.

Existing old layers

- Remove old, loose layers.
- Clean with a paint cleaner such as Universol®.
- Sand and prime greyed wood down to healthy wood.
- If necessary, repair and prime.
- After drying, sand and dust off.
- Prime bare parts with SPS Multi-Primer, bleeding wood with SPS Acrylic Primer.
- Lightly sand and dust off after drying.
- Paint over the entire surface.

Existing intact paint layers

- Clean intact coats with a paint cleaner such as Universol® - Sand the surface well.
- Prime with SPS Multi-Primer.
- Lightly sand and dust after drying.
- Paint over the surface.

The systems listed are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

TECHNICAL DATA

Density (g/cm ³):	1.25
Gloss Level:	sps_zijdeglans
Gloss level at 60°:	45-50%
Solids content in volume:	35%

DRY TIMES BY 20° C/RH 50%

Touch dry:	1 hour
Dry to recoat:	16 hours

RECOMMENDED WET FILM THICKNESS

67 µm

RECOMMENDED DRY FILM THICKNESS

23 µm

THEORETICAL CONSUMPTION

Approx 15 m² / l per coat

PRACTICAL CONSUMPTION

The practical yield depends on several factors such as, among others: the nature and structure of the substrate, the processing method, experience of the processor, and the (weather) conditions during application.

SURFACE PREPARATION

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

DIRECTIONS FOR USE

Stir well before use. Apply in 1 or 2 layers with a suitable brush or roller. Waterborne products dry relatively quickly. To avoid deposits, always work wet-on-wet. Do not touch up while drying.

APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors under threat of rain, frost or full sun. Always use the necessary personal protective equipment when applying this product. Alkyd resin-based products have the tendency to yellow in dark surroundings or when covered. In an environment exposed to daylight this phenomenon is much less common. Always ventilate appropriately during application. This product is skin fat resistant. For skin fat resistance of paint layers, the type of surface contamination and exposure time must be taken into account. Regular cleaning with a suitable agent will increase the service life of the paint film.

APPLICATION & THINNING: BRUSH

Ready-to-use.

APPLICATION & THINNING: ROLLER

Ready-to-use.

CLEANING OF EQUIPMENT / SPILLS

Water and soap

REMARKS

Always use the necessary personal protective equipment when processing this product. Alkyd resin-based products have the tendency to yellow in dark surroundings or when covered. In an environment exposed to daylight this phenomenon is much less common. Always ventilate appropriately during application. This product is skin fat resistant. For skin fat resistance of paint layers, the type of surface contamination and exposure time must be taken into account. Regular cleaning with a suitable agent will increase the service life of the paint film.

SHELF LIFE

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Date issued: 27/05/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

