

# SPS



## SATIN PU-A SPRAY

# Sprayable silk gloss paint based on PU-acrylate

- Scratch- and impact resistant
- Skin oils resistant
- Airless and airmix sprayable
- Great freedom of layer thickness
- Very smooth result

# SATIN PU-A SPRAY

## ОПИСАНИЕ

Spray system-compatible, water-based silk gloss paint based on PU-acrylate. Also ideal for application by brush in hard-to-reach areas, such as the rebate sides of tilt and turn windows. Ideal for new builds, maintenance and renovation. Good viscosity, good colour retention, perfect flow properties, creates a washable finish that is resistant to the skin's oils. For interior use.

## ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

SPS Satin PU A Spray can be used as a finishing layer on pre-treated substrates like wood or metal. It has very good coverage properties.

## ПРЕПОРЪЧИТЕЛНА СИСТЕМА

General:

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

Bare untreated wood

- Prime untreated wood with SPS Multi-Primer, bleeding wood with SPS Acrylic Primer.
- Lightly sand and dust-free after drying.
- Paint off opaque coat.

Existing old layers

- Remove old, loose layers.
- Sand and prime greyed wood down to healthy wood.
- If necessary, repair and prime.
- Sand and dust off after drying.
- Prime bare parts with SPS Multi-Primer, bleeding wood with SPS Acrylic Primer.
- Lightly sand and dust off after drying.
- Paint over the entire surface.

Existing intact paint layers

- Clean the intact layers.
- Sand the substrate well.
- Prime with SPS Multi-Primer.
- Lightly sand and dust off after drying.
- Paint over the entire surface.

*The systems listed are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.*

## ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см <sup>3</sup> ):	1.2
Гланцово ниво:	sps_zijdeglans
Гланцово ниво при 60°:	35-50%
Съдържание на сухо вещество (по обем):	35%

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	approx. 1 hour
Сух за употреба:	ca. 1 hour
Готов за повторно нанасяне:	ca. 6 hours

## МОКЪР СЛОЙ

Maximum approx. 250 micrometres. (spraying to coverage)

## СУХ СЛОЙ

Maximum 90 micrometres.

## РАЗХОДНА НОРМА

With spraying application ca. 6 m<sup>2</sup>/L per layer. This number of paints consumption is theoretical.

## КОНСУМАЦИЯ

Depending on circumstances, nature and structure of the substrate paint consumption can be different.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

## НАЧИН НА УПОТРЕБА

Stir very well before use. This product has light thixotropic like properties. After mixing, this product should be uniform and ready for use. Apply in 1 or 2 coats with an airmix system. Waterborn product dry relatively quick. This product can be touched up when the product is still in the wet fase. Do not touch-up during drying.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply when temperatures are lower than +8°C. Paint should only be applied when temperatures of the substrate are at least 3 degrees higher than dew-point. Always take necessary measures in the form of personal protective equipment (filter-mask, safetyglasses, gloves etc.) Always make sure ventilation is sufficient.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Touch up with a brush or rollers can result in differences in structure of the paintfilm and therefor can also result in color differences with the sprayed paintfilm.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Maximum 10% water.

## БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Nozzle opening: 0.009"-0.012

Pressure: Ca. 70 bar

\*With airless application, use a "low-pressure" nozzle. (Like Graco FF-LP nozzle or Wagner HEA nozzle) The proposed settings for spraying this product is a guide. Depending on circumstances these settings need to be adjusted accordingly by the applicator.

Do not spray the paint film to thick. Excessive paint film thickness will result in longer curing times, sagging and possible longer tackyness of the paintfilm. Adjust the workflow to fit the object that is to be painted.

## ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Nozzle opening: 0.009"-0.012

Pressure: Ca. 60 bar

Airpressure: 1-3 bar

Do not spray the paint film to thick. Excessive paint film thickness will result in longer curing times, sagging and possible longer tackyness of the paintfilm. Adjust the workflow to fit the object that is to be painted.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap

Дата на издаване: 27/05/2026

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)



# SATIN PU-A SPRAY

## ЗАБЕЛЕЖКИ

Variances in film thicknes, temperature, air humidity atc. Influence drying times.

## СРОК НА ГОДНОСТ

Minimum of 12 months if stored in dry, cool and frost-free storage.

Дата на издаване: 27/05/2026

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

