

SPS



SATIN SB

Satin top coat paint based on a siliconized alkyd resin

- Perfect flow
- Long-lasting colour retention
- High durability
- Easy to apply with brush
- Attractive satin gloss

SATIN SB

ОПИСАНИЕ

Satin top coat paint based on a siliconized alkyd resin offering long-lasting protection and a durable colour retention. SPS Satin SB paint offers high hiding power, perfect flow and an attractive satin finish. Maximum durability in combination with SPS Primer LS. For exterior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

As a very durable finishing coat on, among other things, pre-treated wooden, metal or plastic substrates. When used in combination with SPS Primer LS, an exterior durability of up to 8 years can be achieved. The durability also depends on the colour, the chosen paint system, the condition of the substrate, glazing sealant joints, condition of the window joints, etc.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

General: The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

Bare untreated wood

- Prime untreated wood with SPS Primer LS.
- Lightly sand and dust-free after drying.
- Paint over the entire surface.

Existing old layers

- Remove old, loose layers.
- Clean with a paint cleaner such as Universol®.
- Sand and prime greyed wood down to healthy wood.
- If necessary, repair and prime.
- After drying, sand and dust off.
- Prime bare parts with SPS Primer LS.
- Lightly sand and dust off after drying.
- Paint over the entire surface.

Existing intact paint layers

- Clean intact coats with a paint cleaner such as Universol®.
- Sand the substrate well.
- Prime with SPS Primer LS.
- Lightly sand and dust after drying.
- Paint over the surface.

The systems listed are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

ТЕХНИЧЕСКИ ДАННИ

| | |
|--|----------------|
| Плътност (г/см³): | 1,20 |
| Гланцово ниво: | sps_zijdeglans |
| Гланцово ниво при 60°: | 45-50% |
| Съдържание на сухо вещество (по обем): | 65% |

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

| | |
|-----------------------------|----------|
| Сух на допир: | 3 hours |
| Готов за повторно нанасяне: | 20 hours |

МОКЪР СЛОЙ

60 µm

СУХ СЛОЙ

40 µm

РАЗХОДНА НОРМА

16 m² /liter per coat

КОНСУМАЦИЯ

The practical yield depends on several factors such as, among others: the nature and structure of the substrate, the processing method, experience of the processor, and the (weather) conditions during application.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners.

НАЧИН НА УПОТРЕБА

Stir well before use. Apply in 1 or more layers with a suitable brush or roller. Observe the drying time between the two layers of Satin SB. To avoid deposits, always work wet-on-wet. Do not touch up while drying. Lightly sand and dust down between coats.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors in rain, frost or full sun. Always use necessary personal protective equipment when applying this product. Always ventilate appropriately during application. Alkyd resin-based products have the tendency to yellow in dark surroundings or when covered. In an environment exposed to daylight this phenomenon is much less common.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Ready-made.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Ready-made.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

White spirit or brush cleaner.

ЗАБЕЛЕЖКИ

Variations in layer thickness, temperature, humidity, etc. affect the drying time. Lower temperature and higher humidity may delay drying.

СРОК НА ГОДНОСТ

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Дата на издаване: 27/05/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя съдържанието на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

