SPACHTELPUTZ SB

permeable decorative exterior grain plaster

- Low water absorption
- High vapor permeability
- Optimal weather resistance
- Siliconized
- Easy application

SPACHTELPUTZ SB

ОПИСАНИЕ
Durable, highly adhesive decorative plaster with a regular grain structure, based on siliconized synthetic resin dispersion. Features low water absorption and high vapor permeability. Very easy to apply. For exterior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА
As a decorative finish on all smooth and flush surfaces. Suitable substrates include: external thermal insulation, concrete, brick, cement and plaster, existing paint layers, gypsum board, fine sanding, etc.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА
New, untreated substrates- Pre-treat highly absorbent substrates completely with SPS Putz-Grund. - Prime stable substrates with SPS Putz-Grund. **Existing substrates:**- Clean the substrate - Smooth and level the structured substrate - Prime stable substrates with SPS Putz-Grund. **Existing substrates with no load-bearing capacity:**- Thoroughly remove loose layers - Wash off any powdering layers thoroughly and allow to dry. - Repair if necessary - Pre-treat with SPS Fix-Primer - Smooth and level structured substrates - Prime stable load-bearing substrates with SPS Putz-Grund - Prime with SPS Putz-Grund. **Contamination by nicotine, moisture, rust or soot:** Thoroughly clean - Treat the surface/contamination with SPS Iso-Primer - Prime light contamination on stable load-bearing substrates with SPS Putz-Grund Iso. The above systems are general descriptions for the most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	2.0
Гланцово ниво при 60º:	matt
gloss_level_85:	mat
Съдържание на сухо вещество (по обем):	86%

ВРЕМЕ ЗА СУШЕНЕ ДО 20º C/RH 50%

Готов за повторно нанасяне:	12
group_dry_40_full_cure:	Several days

РАЗХОДНА НОРМА
1.2 mm: approx. 2.5 kg/m², 1.5 mm Fine: approx. 3 kg/m²

КОНСУМАЦИЯ
The stated yield is theoretical. Actual consumption depends on the nature and structure of the substrate and the processing method.

ПОДГОТОВКА НА ПОВЪРХНОСТТА
The substrate must be smooth and even. The substrate must also be load-bearing, fully bonded, clean, dry, dust- and grease-free. Tears and cracks must be repaired. Remove and/or repair loose and unstable layers. Before applying SPS decorative plasters, first pre-treat with SPS Putz-Grund. Consult the Surface Assessment Criteria for exterior plastering and the Surface Assessment Criteria for interior plastering to determine whether the surface is sufficiently smooth and level to be finished with SPS ornamental plaster.

НАЧИН НА УПОТРЕБА
Pre-mix buckets together in a tub and mix well before use. If necessary, dilute with up to 5% water. Apply evenly to grain thickness with a stainless steel trowel. Then texture with a plastic trowel in a circular motion until a flat, regular grain structure is obtained. During structuring, regularly remove excess sludge on the plastic trowel. This product can also be sprayed with, for example, a funnel gun, worm pump or other suitable spraying equipment. This creates a coarser/ rougher texture. When spraying textured materials such as decorative plasters, always select the correct nozzle opening: at least 3x maximum grain size.

УСЛОВИЯ ЗА НАНАСЯНЕ
Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors under threat of rain, frost, or in full sunlight.

GROUP_APPL_THINNING_50_RAKE_TROWEL
Maximum 5% clean water.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ
Water and soap

ЗАБЕЛЕЖКИ
Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always ventilate appropriately during application. Slight colour deviations are possible due to the use of natural raw materials. Therefore buckets with different batch numbers must be mixed first in a quantity to cover an entire section of wall from corner to corner. Take any remains or leftover product and the packaging to a collection point for hazardous or special waste.

СРОК НА ГОДНОСТ
Minimum 12 months in well-sealed original container in dry, cool, and frost-free place.

Дата на издаване: 19/06/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu