

SPS



SPACHTELPUTZ SB

permeable decorative exterior grain plaster

- Geringe Wasseraufnahme
- Hohe Dampfdurchlässigkeit
- Optimal wetterbeständig
- Silikonisiert
- Leichte Verarbeitung

SPACHTELPUTZ SB

BESCHREIBUNG

Haltbarer, hervorragend haftender dekorativer Putz mit regelmäßiger Kornstruktur, auf Basis silikonisierter Kunstharzdispersion. Mit geringer Wasseraufnahme und hoher Wasserdampfdurchlässigkeit. Sehr leicht zu verarbeiten. Für den Außenbereich.

EMPFOHLENE VERWENDUNG

As a decorative finish on all smooth and flush surfaces. Suitable substrates include: external thermal insulation, concrete, brick, cement and plaster, existing paint layers, gypsum board, fine sanding, etc.

EMPFOHLENES SYSTEM

New, untreated substrates - Pre-treat highly absorbent substrates completely with SPS Putz-Grund. - Prime stable substrates with SPS Putz-Grund. **Existing substrates**:- Clean the substrate - Smooth and level the structured substrate - Prime stable substrates with SPS Putz-Grund. **Existing substrates with no load-bearing capacity**:- Thoroughly remove loose layers - Wash off any powdering layers thoroughly and allow to dry. - Repair if necessary - Pre-treat with SPS Fix-Primer - Smooth and level structured substrates - Prime stable load-bearing substrates with SPS Putz-Grund - Prime with SPS Putz-Grund. **Contamination by nicotine, moisture, rust or soot**: Thoroughly clean - Treat the surface/contamination with SPS Iso-Primer - Prime light contamination on stable load-bearing substrates with SPS Putz-Grund Iso. The above systems are general descriptions for the most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

TECHNISCHE DATEN

Dichte (g/cm ³):	2.0
Glanzgrad bei 60°:	matt
Glanzgrad bei 85°:	mat
Feststoffgehalt in Volume:	86%

TROCKENZEITEN BEI 20°C/RF 50%

Überstreichbar:	12
Durchgehärtet:	Several days

THEORETISCHE ERGIEBIGKEIT

1.2 mm: approx. 2.5 kg/m², 1.5 mm Fine: approx. 3 kg/m²

PRAKTISCHE ERGIEBIGKEIT

The stated yield is theoretical. Actual consumption depends on the nature and structure of the substrate and the processing method.

UNTERGRUNDVORBEREITUNG

The substrate must be smooth and even. The substrate must also be load-bearing, fully bonded, clean, dry, dust- and grease-free. Tears and cracks must be repaired. Remove and/or repair loose and unstable layers. Before applying SPS decorative plasters, first pre-treat with SPS Putz-Grund. Consult the Surface Assessment Criteria for exterior plastering and the Surface Assessment Criteria for interior plastering to determine whether the surface is sufficiently smooth and level to be finished with SPS ornamental plaster.

HINWEISE ZUR VERARBEITUNG

Pre-mix buckets together in a tub and mix well before use. If necessary, dilute with up to 5% water. Apply evenly to grain thickness with a stainless steel trowel. Then texture with a plastic trowel in a circular motion until a flat, regular grain structure is obtained. During structuring, regularly remove excess sludge on the plastic trowel. This product can also be sprayed with, for example, a funnel gun, worm pump or other suitable spraying equipment. This creates a coarser/ rougher texture. When spraying textured materials such as decorative plasters, always select the correct nozzle opening: at least 3x maximum grain size.

ANWENDUNGSBEDINGUNGEN

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors under threat of rain, frost, or in full sunlight.

VERDÜNNUNG & ANWENDUNG: RAKEL/KELLE

Maximum 5% clean water.

REINIGUNG DER ARBEITSGERÄTE / SPRITZER

Water and soap

BEMERKUNGEN

Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always ventilate appropriately during application. Slight colour deviations are possible due to the use of natural raw materials. Therefore buckets with different batch numbers must be mixed first in a quantity to cover an entire section of wall from corner to corner. Take any remains or leftover product and the packaging to a collection point for hazardous or special waste.

LAGERFÄHIGKEIT

Minimum 12 months in well-sealed original container in dry, cool, and frost-free place.

Ausgabedatum: 26/05/2026

Verfügbare Farben und Packungsgrößen: Bitte beziehen Sie sich auf die jeweilige Produktseite auf www.rust-oleum.eu für eine Übersicht der aktuell verfügbaren Farben und Größen verpacken.

Haftungsausschluss: Die hierin enthaltenen Informationen wurden nach bestem Wissen wahrheitsgetreu und präzise und im guten Glauben zusammengestellt. Wir übernehmen aber keine Haftung. Wir gehen davon aus, dass sich der Anwender eigenverantwortlich über die Eignung unserer Produkte für seine individuelle Zweckbestimmung informiert hat. Rust-Oleum Europe übernimmt keinerlei Haftung für Folgeschäden oder mittelbare Schäden. Die Produkte müssen gelagert, gehandhabt und unter Bedingungen verwendet werden, die den Empfehlungen von Rust-Oleum Europe entsprechen, die in der neuesten Ausgabe des Produktdatenblatts angegeben sind. Der Anwender muss sicherstellen, dass er die neueste Ausgabe besitzt. Die neuesten Ausgaben des Produktdatenblatts können kostenlos auf www.rust-oleum.eu heruntergeladen oder bei unserer Kundendienstabteilung angefordert werden. Rust-Oleum Europe behält sich das Recht vor, die Eigenschaften seiner Produkte ohne vorherige Ankündigung zu ändern.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

