

SPS



TRANSPARANT UV

High-gloss transparent top coat based on an alkyd resin

- Protects against UV radiation
- Moisture regulating
- Accentuates the wood grain
- High coating thickness
- Excellent weather resistance

TRANSPARENT UV

ОПИСАНИЕ

Extra durable, moisture regulating and high-gloss transparent top coat paint for exterior use, based on an alkyd resin. High coating thickness and UV filter for long-lasting protection from wood. Accentuates the grain. For exterior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

Due to the special UV filter, suitable as a transparent primer, pre-coat and top coat on wooden substrates. Despite containing a UV filter, colourless SPS Lacquer Transparent UV is more sensitive to weather than coloured Lacquer Transparent because it does not contain any pigments.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

General: The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage. Always sand in the direction of the grain.

Exposed/untreated wood

- Clean the entire surface using SPS Paint cleaner.
- Sand lightly in the direction of the grain and wipe off any dust residue.

Existing old coats

- Thoroughly remove loose coats.
- Clean the complete surface with SPS Paint cleaner, sand in the direction of the grain and remove any sanding dust.
- Sand decayed wood down in the direction of the grain until you reach healthy wood.

Existing intact coats of paint

- Clean the intact coats of paint with SPS Paint cleaner, sand in the direction of the grain and remove any sanding dust.
- Sand decayed wood down in the direction of the grain until you reach healthy wood.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³):	0.95
Гланцово ниво:	sps_hoogglans
Гланцово ниво при 60°:	87-80%
Съдържание на сухо вещество (по обем):	52%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	4 hours
Готов за повторно нанасяне:	18 hours

МОКЪР СЛОЙ

63 µm

СУХ СЛОЙ

33 µm

РАЗХОДНА НОРМА

Approx. 14 - 16 m²/litre per coat

КОНСУМАЦИЯ

The actual coverage depends on the nature and the structure of the surface and the application method.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners. Always sand in the direction of the grain.

НАЧИН НА УПОТРЕБА

Stir thoroughly prior to use. Apply in 1 or more coats in the direction of the grain using a suitable (flat) brush. Always work wet-on-wet to prevent marks in the paint. Do not touch up when drying. Lightly sand in the direction of the grain in between coats and wipe off any dust residue before applying the next coat.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Always ventilate appropriately when applying. Products based on alkyd resins tend to yellow in a dark environment or when covered. In an environment where they are exposed to daylight, this tendency to yellow is much reduced.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Ready-to-use.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Ready-to-use.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

White spirit or cleaner

ЗАБЕЛЕЖКИ

Variations in coating thickness, temperature, humidity, etc. affect the drying time.

СРОК НА ГОДНОСТ

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Дата на издаване: 27/05/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителите е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя своите свойства на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

