

SPS



TRANSPARENT UV

High-gloss transparent top coat based on an alkyd resin

- Protects against UV radiation
- Moisture regulating
- Accentuates the wood grain
- High coating thickness
- Excellent weather resistance

TRANSPARENT UV

DESCRIPTION

Extra durable, moisture regulating and high-gloss transparent top coat paint for exterior use, based on an alkyd resin. High coating thickness and UV filter for long-lasting protection from wood. Accentuates the grain. For exterior use.

RECOMMENDED USE

Due to the special UV filter, suitable as a transparent primer, pre-coat and top coat on wooden substrates. Despite containing a UV filter, colourless SPS Lacquer Transparent UV is more sensitive to weather than coloured Lacquer Transparent because it does not contain any pigments.

RECOMMENDED SYSTEM

General: The surface must be capable of supporting the paint, clean, dry and free of dust or grease. Slightly round off sharp edges to obtain good edge coverage. Always sand in the direction of the grain.

Exposed/untreated wood

- Clean the entire surface using SPS Paint cleaner.
- Sand lightly in the direction of the grain and wipe off any dust residue.

Existing old coats

- Thoroughly remove loose coats.
- Clean the complete surface with SPS Paint cleaner, sand in the direction of the grain and remove any sanding dust.
- Sand decayed wood down in the direction of the grain until you reach healthy wood.

Existing intact coats of paint

- Clean the intact coats of paint with SPS Paint cleaner, sand in the direction of the grain and remove any sanding dust.
- Sand decayed wood down in the direction of the grain until you reach healthy wood.

The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

TECHNICAL DATA

Density (g/cm ³):	0.95
Gloss Level:	sps_hoogglans
Gloss level at 60°:	87-80%
Solids content in volume:	52%

DRY TIMES BY 20° C/RH 50%

Touch dry:	4 hours
Dry to recoat:	18 hours

RECOMMENDED WET FILM THICKNESS

63 µm

RECOMMENDED DRY FILM THICKNESS

33 µm

THEORETICAL CONSUMPTION

Approx. 14 - 16 m²/litre per coat

PRACTICAL CONSUMPTION

The actual coverage depends on the nature and the structure of the surface and the application method.

SURFACE PREPARATION

The substrate must be load-bearing, clean, dry, dust- and grease-free. For good edge coverage, slightly round off sharp corners. Always sand in the direction of the grain.

DIRECTIONS FOR USE

Stir thoroughly prior to use. Apply in 1 or more coats in the direction of the grain using a suitable (flat) brush. Always work wet-on-wet to prevent marks in the paint. Do not touch up when drying. Lightly sand in the direction of the grain in between coats and wipe off any dust residue before applying the next coat.

APPLICATION CONDITIONS

Do not apply at temperatures below +8°C. Only apply if the surface temperature is at least 3°C above the dew point temperature. Do not apply outdoors when it is likely to rain, when frost is expected or in direct sunlight. Always use the required personal protective equipment when applying this product. Always ventilate appropriately when applying. Products based on alkyd resins tend to yellow in a dark environment or when covered. In an environment where they are exposed to daylight, this tendency to yellow is much reduced.

APPLICATION & THINNING: BRUSH

Ready-to-use.

APPLICATION & THINNING: ROLLER

Ready-to-use.

CLEANING OF EQUIPMENT / SPILLS

White spirit or cleaner

REMARKS

Variations in coating thickness, temperature, humidity, etc. affect the drying time.

SHELF LIFE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date issued: 27/05/2026

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

