



SPS



UNITEX 1515 MATT

Universally applicable wall paint



- Extra matt
- Optimal flow
- Good coverage
- Good washability
- Low odour

UNITEX 1515 MATT

ОПИСАНИЕ

Extra matt, well-covering, universal wall paint based on synthetic resin dispersion. Excellent application properties, optimal flow and breathability. Suitable for finishing walls and ceilings in dry rooms. For interior use.

ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

As a durable smooth finish on mineral substrates indoors. Suitable substrates include: existing wall paint layers, cement and plaster, concrete, brick, plasterboard, etc. Also suitable for painting glass fabric.

ПРЕПОРЪЧИТЕЛНА СИСТЕМА

New, untreated substrates- Prepare (strongly) absorbent substrates with SPS Fix-Primer - Clean powdery substrates thoroughly. Pre-treat with Fix-Primer after drying. - Paint off opaque surfaces after drying. **Existing intact wall paint layers**- Thoroughly clean. - Paint off opaque surfaces after drying. **Existing non-bearing wall paint layers**- Remove loose parts. - Thoroughly wash off powdery layers and allow to dry. - Carry out any repairs. - Pre-treat with SPS Fix-Primer - Once dry, paint over the entire surface. **Contamination by nicotine, moisture, rust or soot**- Thoroughly clean - Treat the surface/contamination with SPS Iso-Primer - Once dry, paint over the entire surface. The systems mentioned are general descriptions for the most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см³): 1,54
Гланцово ниво: extra_matt
gloss_level_85: 5%, extra matt
Съдържание на сухо вещество (по обем): 41%

ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир: 2 hours
Готов за повторно нанасяне: 4 - 6 hours

МОКЪР СЛОЙ

Approx. 143 micrometres.

СУХ СЛОЙ

Approx. 59 micrometres.

РАЗХОДНА НОРМА

Approx. 7 m² /l per coat. The stated yield is theoretical.

КОНСУМАЦИЯ

Actual consumption depends on the nature and structure of the substrate and the processing method.

ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

НАЧИН НА УПОТРЕБА

Stir well before use. If necessary, dilute the first coat with up to 10% water. Apply with a suitable brush, roller or sprayer. Always work wet-on-wet to avoid swelling. Re-roll all surfaces in the same direction. Do not touch up while drying.

УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Maximum 10% water.

НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Maximum 10% water.

БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Airless Nozzle: 0.015"-0.017", Pressure: approx.180 bar, Dilute: Maximum 5% water.
Airmix Nozzle: 0.015-0.017", Pressure: approx.160 bar, Air pressure: approx. 1.5 bar, Dilute: Maximum 5% water.

The specified settings for spraying this product are a starting point. Depending on site conditions, settings will have to be determined by the applicator.

ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap.

ЗАБЕЛЕЖКИ

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always ventilate appropriately during processing. Take this material and its container to hazardous or special waste collection point.

СРОК НА ГОДНОСТ

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Дата на издаване: 27/05/2026

Налични цветове и размери на опаковките: Моля, вижте съответната продуктова страница на www.rust-oleum.eu, за да се запознаете с актуалните налични цветове и размери на опаковките.

Отказ от отговорност: Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителя е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от www.rust-oleum.eu или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.
Europalaan 9
5232 BC 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu

