

# SPS



## UNITEX 2525 MATT

---



- Super coverage
- Matt
- Economical
- Good washability
- Solvent-free and low-odour

# UNITEX 2525 MATT

## ОПИСАНИЕ

Super opaque, matt wall paint based on synthetic resin dispersion. Usually covers in one coat, saving one working pass. Low-odour, breathable and washable. Particularly intended for durable finishing of interior walls and ceilings. For interior use.

## ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

As a durable smooth finish on mineral substrates indoors. Suitable substrates include: existing wall paint coats, cement and plaster, concrete, brick, plasterboard, etc.

## ПРЕПОРЪЧИТЕЛНА СИСТЕМА

**New, untreated substrates** - Prime highly absorbent substrates completely with SPS Fix primer. - Clean powdery substrates thoroughly. Pre-treat with SPS Fix Primer after drying. - After drying, paint over the entire surface. **Existing intact wall paint layers** - Thoroughly clean. - Paint over the surface after drying. Remove loose particles. - Thoroughly wash off any powdering layers and allow to dry. - Make any necessary repairs. - Pre-treat with SPS Fix-Primer. - Paint over the surface after drying. **Contamination by nicotine, moisture, rust or soot** - Clean thoroughly. - Treat the surface/contamination with SPS Iso-Primer. - Paint over the surface after drying. The above systems are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

## ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см <sup>3</sup> ):	1,47
Гланцово ниво:	Мат
gloss_level_85:	10%, matt.
Съдържание на сухо вещество (по тегло):	35

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир:	2 hours
Готов за повторно нанасяне:	4 - 6 hours

## РАЗХОДНА НОРМА

Approx. 9 m<sup>2</sup> / ltr. per coat. The stated yield is theoretical.

## КОНСУМАЦИЯ

Actual consumption depends on the nature and structure of the substrate and the processing method.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, completely sealed, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers.

## НАЧИН НА УПОТРЕБА

Stir well before use. If necessary, dilute the first coat with up to 10% water. Apply with a suitable brush, roller or sprayer. Always work wet-on-wet in order to avoid deposits. Re-roll all webs in the same direction. Do not touch up while drying.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Maximum 10% water.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Maximum 10% water.

## ВЪЗДУШНО РАЗПРАШВАНЕ (AIR-ATOMISED SPRAY)

Airless Nozzle: 0.017"-0.021", Pressure: approx.200 bar, Dilute: Maximum 5% water.  
Airmix Nozzle: 0.017-0.021", Pressure: approx.120 bar, Air pressure: approx. 2 bar, Dilute: Maximum 5% water.

The specified settings for spraying this product are a starting point. Depending on site conditions, settings will have to be determined by the applicator.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap.

## ЗАБЕЛЕЖКИ

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always ventilate appropriately during processing. Take this material and its container to hazardous or special waste collection point.

## СРОК НА ГОДНОСТ

Minimum 12 months in tightly closed original container in dry, cool and frost-free place.

Дата на издаване: 27/05/2026

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителя е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

