



# SPS



## UNITEX 5050 MAT

### **matt, 100% acrylic facade paint**

- Excellent coverage
- Scrub-resistant class 1 (DIN EN 13300)
- 100% acrylic
- Optimal flow
- Good weather resistance

# UNITEX 5050 MAT

## ОПИСАНИЕ

Very high-quality, excellently covering, matte, 100% acrylic wall paint. Excellent weather resistance and scrub-resistant. Perfectly suited for durable finishing of exterior facades and interior walls. Also applicable in damp rooms. For interior and exterior use

## ПРЕПОРЪЧИТЕЛНА УПОТРЕБА

For a durable finish on exterior facades and interior walls, also suitable for damp rooms. Perfect for interior and exterior paintwork with high demands. Suitable substrates include: existing wall paint layers, cement and plaster, concrete, brick, etc.

## ПРЕПОРЪЧИТЕЛНА СИСТЕМА

**New, untreated substrates** - Prime highly absorbent substrates completely with SPS Fix-Primer. - Clean powdery substrates thoroughly. Pre-treat with SPS Fix-Primer after drying. - Paint over **existing intact wall paint layers** - Clean. - If necessary, apply an intermediate coat of SPS Wall-Primer. - Paint off opaquely after drying. **Existing non-load-bearing wall paint layers** - Remove loose particles. - Wash off powdery layers thoroughly and allow to dry. - Carry out any necessary repairs. - Pre-treat with SPS Fix-Primer. - After drying, paint over the surface. **Contamination by nicotine, moisture, rust or soot** - Clean thoroughly. - Treat the surface/pollution with SPS Iso-Primer. - After drying, paint over the surface. The systems listed are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

## ТЕХНИЧЕСКИ ДАННИ

Плътност (г/см<sup>3</sup>): 1,44  
Гланцово ниво: extra\_matt  
Съдържание на сухо вещество (по обем): 42%

## ВРЕМЕ ЗА СУШЕНЕ ДО 20° C/RH 50%

Сух на допир: 2 hours  
Готов за повторно нанасяне: 4 - 6 hours

## МОКЪР СЛОЙ

Approx. 111 micrometres.

## СУХ СЛОЙ

Approx. 46 micrometres.

## РАЗХОДНА НОРМА

Approx. 9 m<sup>2</sup> / litre per coat.

## КОНСУМАЦИЯ

Actual consumption depends on the nature and structure of the substrate and the processing method.

## ПОДГОТОВКА НА ПОВЪРХНОСТТА

The substrate must be load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers. For exterior use, remove all algae and moss deposits.

## НАЧИН НА УПОТРЕБА

Stir well before use. If necessary, dilute the first coat with up to 10% water. Apply with a suitable brush, roller or sprayer. Always work wet-on-wet to avoid swelling. Re-roll all surfaces in the same direction. Do not touch up while drying.

## УСЛОВИЯ ЗА НАНАСЯНЕ

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors under threat of rain, frost or full sun.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ЧЕТКА

Maximum 10% water.

## НАНАСЯНЕ И РАЗРЕЖДАНЕ: ВАЛЯК

Maximum 10% water.

## БЕЗВЪЗДУШНО ПРЪСКАНЕ (AIRLESS SPRAY)

Airless: Nozzle opening: 0.017-0.019", Pressure: approx. 180 bar, Dilute: Maximum 10% water.

Airmix: Nozzle opening: 0.017-0.019", Pressure: >120 bar, Air pressure: approx. 2 bar, Dilute: Maximum 10% water.

The specified settings for spraying this product are a starting point. Depending on site conditions, settings will have to be determined by the applicator.

## ПОЧИСТВАНЕ НА ОБОРУДВАНЕ И РАЗЛИВИ

Water and soap.

## ЗАБЕЛЕЖКИ

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always provide adequate ventilation during application. Take this material and its container to collection point for hazardous or special waste. With (dark-coloured) matt wall paints, clearly visible gloss traces may appear after the first rain shower, also known as snail marks. These are auxiliary substances and contents emerging from the still fresh paint film. They are then visible as yellowish, transparent, slightly shiny and sticky streaks. These contents are water-soluble and will usually be washed away after a few rain showers. If necessary, rinsing with clean water can speed up the cleaning of the façade. Natural washing out is preferred. The paint layer will then regain an even colour, the gloss streaks will fade and disappear. This phenomenon does not otherwise affect the quality of the paint layer.

## СРОК НА ГОДНОСТ

Minimum 12 months in tightly closed original container in dry, cool, frost-free place.

Дата на издаване: 27/05/2026

**Налични цветове и размери на опаковките:** Моля, вижте съответната продуктова страница на [www.rust-oleum.eu](http://www.rust-oleum.eu), за да се запознаете с актуалните налични цветове и размери на опаковките.

**Отказ от отговорност:** Информацията, съдържаща се в този документ, доколкото ни е известно, е вярна и точна и се предоставя добросъвестно, но без гаранция. Счита се, че потребителят се е уверил самостоятелно в пригодността на нашите продукти за неговата/нейната конкретна цел. При никакви обстоятелства Rust-Oleum Europe не носи отговорност за последващи или случайни щети. Продуктите трябва да се съхраняват, обработват и нанасят при условия, съответстващи на препоръките на Rust-Oleum Europe, подробно описани в последното копие на информационния лист на продукта. Отговорност на потребителя е да се уверят, че разполагат с актуалното копие. Последните копия на информационния лист за продукта са на разположение безплатно и могат да бъдат изтеглени от [www.rust-oleum.eu](http://www.rust-oleum.eu) или при запитване до нашия отдел за обслужване на клиенти. Rust-Oleum Europe си запазва правото да променя свойствата на своите продукти без предварително уведомление.

Rust-Oleum Netherlands B.V.  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

Tor Coatings Ltd (Rust-Oleum Industrial)  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

Rust-Oleum France S.A.S.  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

N.V. Martin Mathys S.A.  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

