



# SPS



## UNITEX 5050 MAT

# matt, 100% acrylic facade paint



- Ausgezeichnete Witterungsbeständigkeit
- Wasserdampfdurchlässig
- Scheuerbeständig, Klasse 1 (DIN EN 13300)

# UNITEX 5050 MAT

## BESCHREIBUNG

Sehr hochwertige, hervorragend deckende, matte, 100 % Acryl-Wandfarbe. Ausgezeichnete Witterungsbeständigkeit und scheuerbeständig. Besonders geeignet für die dauerhafte Beschichtung von Außenfassaden und Innenwänden. Auch in feuchten Räumen anwendbar. Für innen und außen.

## EMPFOHLENE VERWENDUNG

For a durable finish on exterior facades and interior walls, also suitable for damp rooms. Perfect for interior and exterior paintwork with high demands. Suitable substrates include: existing wall paint layers, cement and plaster, concrete, brick, etc.

## EMPFOHLENES SYSTEM

**New, untreated substrates** - Prime highly absorbent substrates completely with SPS Fix-Primer. - Clean powdery substrates thoroughly. Pre-treat with SPS Fix-Primer after drying. - Paint over **existing intact wall paint layers** - Clean. - If necessary, apply an intermediate coat of SPS Wall-Primer. - Paint off opaquely after drying. **Existing non-load-bearing wall paint layers** - Remove loose particles. - Wash off powdery layers thoroughly and allow to dry. - Carry out any necessary repairs. - Pre-treat with SPS Fix-Primer. - After drying, paint over the surface. **Contamination by nicotine, moisture, rust or soot** - Clean thoroughly. - Treat the surface/pollution with SPS Iso-Primer. - After drying, paint over the surface. The systems listed are general descriptions for most common substrates. For specific applications and/or detailed advice, please contact SPS bv.

## TECHNISCHE DATEN

Dichte (g/cm<sup>3</sup>): 1,44  
Glanzgrad: Extra-Matt  
Feststoffgehalt in Volume: 42%

## TROCKENZEITEN BEI 20°C/RF 50%

Klebfrei: 2 hours  
Überstreichbar: 4 - 6 hours

## EMPFOHLENE NASSE SCHICHTDICKE

Approx. 111 micrometres.

## EMPFOHLENE TROCKENSCHICHTDICKE

Approx. 46 micrometres.

## THEORETISCHE ERGIEBIGKEIT

Approx. 9 m<sup>2</sup> / litre per coat.

## PRAKTISCHE ERGIEBIGKEIT

Actual consumption depends on the nature and structure of the substrate and the processing method.

## UNTERGRUNDVORBEREITUNG

The substrate must be load-bearing, fully bonded, clean, dry, dust- and grease-free. Repair cracks and fissures. Remove and/or repair loose and unstable layers. For exterior use, remove all algae and moss deposits.

## HINWEISE ZUR VERARBEITUNG

Stir well before use. If necessary, dilute the first coat with up to 10% water. Apply with a suitable brush, roller or sprayer. Always work wet-on-wet to avoid swelling. Re-roll all surfaces in the same direction. Do not touch up while drying.

## ANWENDUNGSBEDINGUNGEN

Do not apply at temperatures below +8°C. Only apply when the temperature of the substrate is at least 3°C above the dew point temperature. Do not apply outdoors under threat of rain, frost or full sun.

## VERDÜNNUNG & ANWENDUNG: PINSEL

Maximum 10% water.

## VERDÜNNUNG & ANWENDUNG: ROLLER

Maximum 10% water.

## VERDÜNNUNG & ANWENDUNG: AIRLESS SPRITZEN

Airless: Nozzle opening: 0.017-0.019", Pressure: approx. 180 bar, Dilute: Maximum 10% water.

Airmix: Nozzle opening: 0.017-0.019", Pressure: >120 bar, Air pressure: approx. 2 bar, Dilute: Maximum 10% water.

The specified settings for spraying this product are a starting point. Depending on site conditions, settings will have to be determined by the applicator.

## REINIGUNG DER ARBEITSGERÄTE / SPRITZER

Water and soap.

## BEMERKUNGEN

The values listed in this technical data sheet are determined on the basis of DIN EN 13300. Always use the necessary personal protective equipment when handling this product. Do not inhale product vapour and spray mist. Always provide adequate ventilation during application. Take this material and its container to collection point for hazardous or special waste. With (dark-coloured) matt wall paints, clearly visible gloss traces may appear after the first rain shower, also known as snail marks. These are auxiliary substances and contents emerging from the still fresh paint film. They are then visible as yellowish, transparent, slightly shiny and sticky streaks. These contents are water-soluble and will usually be washed away after a few rain showers. If necessary, rinsing with clean water can speed up the cleaning of the façade. Natural washing out is preferred. The paint layer will then regain an even colour, the gloss streaks will fade and disappear. This phenomenon does not otherwise affect the quality of the paint layer.

## LAGERFÄHIGKEIT

Minimum 12 months in tightly closed original container in dry, cool, frost-free place.

Ausgabedatum: 26/05/2026

**Verfügbare Farben und Packungsgrößen:** Bitte beziehen Sie sich auf die jeweilige Produktseite auf [www.rust-oleum.eu](http://www.rust-oleum.eu) für eine Übersicht der aktuell verfügbaren Farben und Größen verpacken.

**Haftungsausschluss:** Die hierin enthaltenen Informationen wurden nach bestem Wissen wahrheitsgetreu und präzise und im guten Glauben zusammengestellt. Wir übernehmen aber keine Haftung. Wir gehen davon aus, dass sich der Anwender eigenverantwortlich über die Eignung unserer Produkte für seine individuelle Zweckbestimmung informiert hat. Rust-Oleum Europe übernimmt keinerlei Haftung für Folgeschäden oder mittelbare Schäden. Die Produkte müssen gelagert, gehandhabt und unter Bedingungen verwendet werden, die den Empfehlungen von Rust-Oleum Europe entsprechen, die in der neuesten Ausgabe des Produktdatenblatts angegeben sind. Der Anwender muss sicherstellen, dass er die neueste Ausgabe besitzt. Die neuesten Ausgaben des Produktdatenblatts können kostenlos auf [www.rust-oleum.eu](http://www.rust-oleum.eu) heruntergeladen oder bei unserer Kundendienstabteilung angefordert werden. Rust-Oleum Europe behält sich das Recht vor, die Eigenschaften seiner Produkte ohne vorherige Ankündigung zu ändern.

**Rust-Oleum Netherlands B.V.**  
Europalaan 9  
5232 BC 's-Hertogenbosch  
The Netherlands  
T: +31 (0) 165 593 636  
F: +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T: +44 (0)1914 113 146  
F: +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T: +33(0) 130 40 00 44  
F: +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T: +32 (0) 13 460 200  
F: +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

